

51597

POLYESTER FILM / GLASS FILAMENT REINFORCED ELECTRICAL TAPE

DESCRIPTION

#51597 has high tensile strength, conformable backing and aggressive adhesive for a large variety of insulating and holding applications. This tape is resistant to chemicals, solvents, and aging and offers a high dielectric strength and insulation resistance.

PRODUCT APPLICATIONS

Inter-layer insulation, coil outer wraps, tie-downs, lead insulation and protection. Also used on electrical motor and generator binding.



3647 Cortez Road West | Bradenton, FL 34210 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 04/12

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard test. The data should not be considered as specifications.

Backing	Polyester Film / Glass Filament
Backing Thickness	5.5 mil
Adhesive	Acrylic
Color	Clear
Total Thickness	6.5 mil (0.165 mm)
Dielectric Strength ²	5000 Volts
Dielectric Constant	1.82
Temp. Class ²	155° C / F
Insulation Resistance ²	10 ⁴ megohms
Tensile Strength	250 lbs/in (438 N/cm)
Adhesion to Steel	40 oz/in (4.4 N/cm)
Elongation	5%
Electrolytic Corrosion	1.0 Direct/ A, 1*
Flammability	BU 2*
Storage Stability	Excellent
Solvent Resistance	Excellent
Moisture Resistance	Excellent
UL File #	E20780
CSA File #	LR94980

*VDE 0340

