




C055121A2

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



| MPP Permeability (μ) | A_L (nH/T ²) | Core Marking | | | Coating Color |
|----------------------------|----------------------------|--------------|-------------|------------------|---------------|
| | | Lot Number | Part Number | Inductance Grade | |
| 60 | 35 ± 8% | XXXXXX | 55121A2 | X | Gray |

| Dimensions | Uncoated | | Coated Limits | | Packaging |
|------------|----------|-------|---------------|-------|--|
| | (mm) | (in) | (mm) | (in) | |
| OD (A) | 16.6 | 0.653 | 17.3 | 0.680 | Bulk Pack 4 bags/box Box Qty= 2000 pcs |
| ID (B) | 10.2 | 0.400 | 9.52 | 0.375 | |
| HT (C) | 6.35 | 0.250 | 7.12 | 0.280 | |

| Electrical Characteristics | | | Physical Characteristics | | | | | | |
|---|----------------------|------|---|-------------------------|---|---|---------------------------------|--|------------|
| Watt Loss @ 100 kHz, 100mT max(mW/cm ³) | DC Bias min (A-T/cm) | | Voltage Breakdown wire to wire min (V _{AC}) | Break Strength min (kg) | Window Area W _A (mm ²) | Cross Section A _e (mm ²) | Path Length L _e (mm) | Volume V _e (mm ³) | Weight (g) |
| | 80% | 50% | | | | | | | |
| 950 | 39.7 | 74.7 | 1000 | 14 | 71.2 | 19.2 | 41.2 | 791 | 6.4 |

| Winding Information | | | | | Temperature Rating | |
|-------------------------|------|----------------|------|---------------------------------|--------------------|---|
| Winding Length Per Turn | | | | Wound Coil Dimensions (mm) | | Curie Temp: 460 °C |
| Winding Factor | (mm) | Winding Factor | (mm) | Maximum OD (70%) | 23.7 | Coating Temp (Continuous up to): 200 °C |
| | | | | Maximum HT (70%) | 15.2 | |
| 0% | 22.1 | 40% | 27.0 | Surface Area (mm ²) | | Notes: |
| 20% | 24.6 | 45% | 27.7 | Unwound Core | | |
| 25% | 25.2 | 50% | 28.4 | 40% Winding Factor | | |
| 30% | 25.6 | 60% | 29.8 | | | |
| 35% | 26.4 | 70% | 31.5 | | | |

Typical DC Bias Performance

