




Part Number:

MS-039075-2

Revision 2021-Dec-01 - Generated 2021-Dec-01



(If coated, Max./Min. includes coating)

OD	(nom. - bare core) (max.)	9.65 mm 10.29 mm	0.380 in 0.405 in
ID	(nom. - bare core) (min.)	4.78 mm 4.27 mm	0.188 in 0.168 in
HT	(nom. - bare core) (max.)	3.18 mm 3.81 mm	0.125 in 0.150 in
Mass	(approximate)	0.96 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	0.0752 cm ²	
	L_e - Eff. Mag. Path Length	2.18 cm	
	V_e - Eff. Core Volume	0.164 cm ³	
	W_A - Min. Eff. Window Area	0.143 cm ²	
	S_A - Surface Area	3.61 cm ²	
Inductance	μ_i (reference)	75	
	A_L value (nominal)	32 nH/N ²	
	Test Winding	N=45, #30 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.015 V	
Core Loss	AL tolerance	±12%	
	Core Loss(mW/cm ³):	$\frac{f}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B_{pk} expressed in gauss, f expressed in hertz, and:	$a=7.890E+09$, $b=7.111E+08$, $c=8.980E+06$, $d=2.846E-14$	
	B_{pk}	1000 G	
	frequency	50 kHz	
DC Saturation	Core Loss (nominal)	323 mW/cm ³	
	Core Loss (maximum)	372 mW/cm ³	
	$\% \mu_i \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and:	$a=1.000E-02$, $b=3.414E-06$, $c=1.841$, $d=0.000$	
	H_{DC}	80 Oe	
Coating/Pkg	Percent Initial Perm(nom.)	47.9%	
	Percent Initial Perm(min.)	39.6%	
	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
Winding Table	Limit	0.1 mA, 5 s	
	Package Quantity	10,800 Pcs/Box	

Wire Size	AWG	20	22	24	26	28	30	32	34	36	38	40
	mm	0.800	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100	0.080
Single Layer	Turns	11	14	18	23	29	37	47	59	74	93	116
	Rdc(Ω)	5.8 m	11.7 m	23.9 m	48.6 m	97.4 m	197.6 m	399.2 m	796.9 m	1.6	3.2	6.3
Full Winding	Turns	10	16	25	38	59	92	142	219	339	525	813
	Rdc(Ω)	5.2 m	13.4 m	33.2 m	80.2 m	198.1 m	491.3 m	1.2	3.0	7.3	17.9	44.2

