




Part Number:

MS-520090-2

Revision:

2023-Dec-06



(If coated, Max./Min. includes coating)

(if coated, Max./Min. includes coating)			mm	in		
OD	(nom. - bare core)		132.54	5.218		
	(max.)		134.21	5.284		
ID	(nom. - bare core)		78.59	3.094		
	(min.)		77.04	3.033		
HT	(nom. - bare core)		20.32	0.800		
	(max.)		21.72	0.855		
Mass	(approximate)		1,020	grams		
Magnetic Dimensions	A _e - Eff. Mag. Cross Section		5.35	cm ²		
	L _e - Eff. Mag. Path Length		32.429	cm		
	V _e - Eff. Core Volume		173	cm ³		
	W _A - Min. Eff. Window Area		46.6	cm ²		
	s _a - Surface Area		515	cm ²		
	mlt - mean length per turn		13.9	cm		
Inductance	μ _i (reference)		90			
	A _L value (nominal)		187	nH/N ²		
	Test Winding		200 Turns	AWG# 18		
	Frequency		10k	Hz		
	Voltage on Agilent 4284A		4.8	V		
	AL tolerance		±8%			
Core Loss	$\text{Core Loss(mW/cm}^3\text{)}=\frac{a}{Bpk^3}+\frac{b}{Bpk^{2.3}}+\frac{c}{Bpk^{1.65}}+d\cdot Bpk^2\cdot f^2$					
	where <i>B_{pk}</i> expressed in gauss, <i>f</i> expressed in hertz, and: <i>a</i> =7.890E+09, <i>b</i> =7.111E+08, <i>c</i> =8.980E+06, <i>d</i> =2.846E-14					
	B _{pk}	1000		G		
	frequency	50 k		Hz		
	Core Loss (nominal)	323		mW/cm ³		
	Core Loss (maximum)	372		mW/cm ³		
DC Saturation	$\% \mu_i \frac{1}{a+b\cdot H^c}+d$					
	where H expressed in oersteds, and: <i>a</i> =1.000E-02, <i>b</i> =4.807E-05, <i>c</i> =1.349, <i>d</i> =0.000					
	H _{DC}	50		Oe		
	Percent Initial Perm.(nom.)	51.5		%		
	Percent Initial Perm.(min.)	45.4		%		
Coating/Pkg	Coating Type:		Blue Epoxy			
	Voltage Breakdown (min.)		1000 Vrms			
	Limit		0.1 mA, 5 s			
	Package Quantity		6 Pcs/Box			
Winding Table	Wire Size	AWG	8	10	12	
		mm	3.150	2.500	2.000	
	Single Layer	Turns	62	78	98	
		Rdc(Ω)	17.7 m	35.5 m	70.9 m	1
	Full Winding	Turns	244	378	584	
		Rdc(Ω)	69.8 m	172.0 m	422.6 m	

