




Part Number:

MS-521075-2

Revision:

2023-Dec-06



(If coated, Max./Min. includes coating)

(if coated, Max./Min. includes coating)		mm	in			
OD	(nom. - bare core)	132.54	5.218			
	(max.)	134.21	5.284			
ID	(nom. - bare core)	78.59	3.094			
	(min.)	77.04	3.033			
HT	(nom. - bare core)	25.40	1.000			
	(max.)	26.80	1.055			
Mass	(approximate)	1,270	grams			
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	6.71	cm ²			
	L _e - Eff. Mag. Path Length	32.429	cm			
	V _e - Eff. Core Volume	218	cm ³			
	W _A - Min. Eff. Window Area	46.6	cm ²			
	s _a - Surface Area	540	cm ²			
	mlt - mean length per turn	14.9	cm			
Inductance	μ _i (reference)	75				
	A _L value (nominal)	195	nH/N ²			
	Test Winding	200 Turns	AWG# 18			
	Frequency	10k	Hz			
	Voltage on Agilent 4284A	6.0	V			
	AL tolerance	±8%				
Core Loss	$\text{Core Loss(mW/cm}^3\text{)}=\frac{a}{B_{pk}^3}+\frac{b}{B_{pk}^{2.3}}+\frac{c}{B_{pk}^{1.65}}+d\cdot B_{pk}^2\cdot f^2$					
	where <i>B_{pk}</i> expressed in gauss, <i>f</i> expressed in hertz, and: <i>a</i> =7.890E+09, <i>b</i> =7.111E+08, <i>c</i> =8.980E+06, <i>d</i> =2.846E-14					
	B _{pk}	1000	G			
	frequency	50 k	Hz			
	Core Loss (nominal)	323	mW/cm ³			
	Core Loss (maximum)	372	mW/cm ³			
DC Saturation	$\% \mu_i \frac{1}{a+b\cdot H^c}+d$					
	where H expressed in oersteds, and: <i>a</i> =1.000E-02, <i>b</i> =3.414E-06, <i>c</i> =1.841, <i>d</i> =0.000					
	H _{DC}	80	Oe			
	Percent Initial Perm.(nom.)	47.9	%			
	Percent Initial Perm.(min.)	39.6	%			
Coating/Pkg	Coating Type:	Blue Epoxy				
	Voltage Breakdown (min.)	1000 Vrms				
	Limit	0.1 mA, 5 s				
	Package Quantity	6 Pcs/Box				
Winding Table	Wire Size	AWG	8	10	12	
		mm	3.150	2.500	2.000	
	Single Layer	Turns	62	78	98	
		Rdc(Ω)	19.0 m	38.1 m	76.1 m	1
	Full Winding	Turns	244	378	584	
		Rdc(Ω)	74.9 m	184.5 m	453.4 m	

