




Part Number:





MS-028060-2

Revision 2021-Dec-01 - Generated 2021-Dec-01



(If coated, Max./Min. includes coating)

OD	(nom. - bare core)	7.04 mm	0.277 in
	(max.)	7.67 mm	0.302 in
ID	(nom. - bare core)	3.96 mm	0.156 in
	(min.)	3.45 mm	0.136 in
HT	(nom. - bare core)	5.08 mm	0.200 in
	(max.)	5.72 mm	0.225 in
Mass	(approximate)	0.73 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	0.0750 cm ²	
	L_e - Eff. Mag. Path Length	1.68 cm	
	V_e - Eff. Core Volume	0.126 cm ³	
	WA - Min. Eff. Window Area	0.0935 cm ²	
	sa - Surface Area	2.80 cm ²	
Inductance	mlt - mean length per turn	1.74 cm	
	μ_i (reference)	60	
	A_L value (nominal)	33 nH/N ²	
	Test Winding	N=40, #32 AWG	
	Frequency	10 kHz	
Core Loss	Voltage on Agilent 4284A	0.013 V	
	AL tolerance	±12%	
	Core Loss(mW/cm ³):	$\frac{f}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B_{pk} expressed in gauss, f expressed in hertz, and:	$a=7.890E+09, b=7.111E+08, c=8.980E+06, d=2.846E-14$	
	B_{pk}	1000 G	
DC Saturation	frequency	50 kHz	
	Core Loss (nominal)	323 mW/cm ³	
	Core Loss (maximum)	372 mW/cm ³	
	$\% \mu_i \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and:	$a=1.000E-02, b=2.151E-06, c=1.841, d=0.000$	
Coating/Pkg	H_{dc}	100 Oe	
	Percent Initial Perm(nom.)	49.2%	
	Percent Initial Perm(min.)	40.9%	
	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
Winding Table	Limit	0.1 mA, 5 s	
	Package Quantity	12,600 Pcs/Box	
	Wire Size	AWG	22
		mm	0.630
	Single Layer	Turns	11
		Rdc(Ω)	10.1 m
	Full Winding	Turns	10
		Rdc(Ω)	9.2 m



Winding Table	Wire Size	AWG	22	24	26	28	30	32	34	36	38	40	42
		mm	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100	0.080	0.063
	Single Layer	Turns	11	14	18	23	29	37	47	59	75	93	117
		Rdc(Ω)	10.1 m	20.5 m	41.9 m	85.1 m	170.7 m	346.3 m	699.6 m	1.4	2.8	5.6	11.1
Full Winding	Full Winding	Turns	10	16	25	39	60	92	143	222	343	531	821
		Rdc(Ω)	9.2 m	23.4 m	58.2 m	144.3 m	353.1 m	861.1 m	2.1	5.3	12.9	31.8	78.2