




Part Number:

MS-141160-2

Revision:

2023-Dec-06



(If coated, Max./Min. includes coating)

(If coated, Max./Min. includes coating)		mm	in			
OD	(nom. - bare core)	35.81	1.410			
	(max.)	36.63	1.442			
ID	(nom. - bare core)	22.35	0.880			
	(min.)	21.54	0.848			
HT	(nom. - bare core)	10.46	0.412			
	(max.)	11.28	0.444			
Mass	(approximate)	36	grams			
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.678	cm ²			
	L _e - Eff. Mag. Path Length	8.98	cm			
	V _e - Eff. Core Volume	6.09	cm ³			
	W _A - Min. Eff. Window Area	3.64	cm ²			
	s _a - Surface Area	45.6	cm ²			
	mlt - mean length per turn	4.84	cm			
Inductance	μ _i (reference)	160				
	A _L value (nominal)	150	nH/N ²			
	Test Winding	80 Turns	AWG# 22			
	Frequency	10k	Hz			
	Voltage on Agilent 4284A	0.24	V			
	AL tolerance	±8%				
Core Loss	$\text{Core Loss(mW/cm}^3\text{)}=\frac{a}{B_{pk}^3}+\frac{b}{B_{pk}^{2.3}}+\frac{c}{B_{pk}^{1.65}}+d\cdot B_{pk}^2\cdot f^2$					
	where B_{pk} expressed in gauss, f expressed in hertz, and: $a=1.394E+10$, $b=1.034E+09$, $c=1.244E+07$, $d=4.007E-14$					
	B _{pk}	1000	G			
	frequency	50 k	Hz			
	Core Loss (nominal)	276	mW/cm ³			
	Core Loss (maximum)	318	mW/cm ³			
DC Saturation	$\% \mu_i \frac{1}{a+b\cdot H^c}+d$					
	where H expressed in oersteds, and: $a=1.000E-02$, $b=4.439E-05$, $c=1.627$, $d=0.000$					
	H _{DC}	40	Oe			
	Percent Initial Perm.(nom.)	35.8	%			
	Percent Initial Perm.(min.)	29.3	%			
Coating/Pkg	Coating Type:	Blue Epoxy				
	Voltage Breakdown (min.)	1000 Vrms				
	Limit	0.1 mA, 5 s				
	Package Quantity	315 Pcs/Box				
Winding Table	Wire Size	AWG	8	10	12	
		mm	3.150	2.500	2.000	
	Single Layer	Turns	15	20	25	
		Rdc(Ω)	1.5 m	3.2 m	6.3 m	1
	Full Winding	Turns	19	30	46	
		Rdc(Ω)	1.9 m	4.8 m	11.6 m	

