



Iron Powder Core



DT106-XXX



Part No.	AL(nH/N ²)	OD(mm)	ID(mm)	Ht(mm)	le(cm)	Ae(cm ²)	Ve(cm ³)
DT106-2	13.5	26.9	14.5	11.1	6.49	0.659	4.28
DT106-8	45.0						
DT106-18	70.0						
DT106-26	93.0						
DT106-28	30.0						
DT106-30	30.0						
DT106-33	40.0						
DT106-34	40.0						
DT106-35	40.0						
DT106-38	108.0						
DT106-40	81.0						
DT106-52	95.0						

DMEGC MIX NO	Reference Permeability	Temperature Stability	Toroidal Color Code
-2	10	95	Red/Gray
-8	35	255	Yellow/Red
-18	55	385	Green/Red
-26	75	825	Yellow/White
-28	22	415	Gray/Green
-33	33	635	Gray/Yellow
-34	33	565	Gray/Blue
-35	33	665	Yellow/Gray
-38	85	955	Gray/Black
-40	60	950	Green/Yellow
-52	75	650	Green/Blue